



Bunton Bagcrete 30 is a concrete mix for shaft repairs.

FEATURES

- Clean up time is reduced
- Easily applied
- Complies to AAC 711/3 standards

BENEFITS

- All in a bag
- Just add water
- Required quantity can be produced on site

STORAGE

- Store bags in dry areas / under cover
- Do not stack more than 9 high
- Do not use broken bags
- Use on a first-in-first-out basis

SPECIFICATION

This product, if correctly applied, will achieve a compressive strength of 5MPa in just 2 hours, 15 MPa in one day, 24 MPa in one week and 30MPa in 28 days.

MIXING INSTRUCTION

Prior to use, wash substrate with running water.

1. Open aggregate and cement bag.
2. Empty contents into a blender, or hand mix dry material thoroughly.
3. Start machine.
4. Place mixed material in dry shotcrete machine.
5. Adjust water and air at nozzle to achieve good shotcrete.

RISK ASSESSMENT / SAFETY (PPE)

- Use personal protective clothing e.g. gloves, goggles, overall, gumboots and dust masks.
- If product gets into eyes, rinse thoroughly with running water for 15 minutes.
- Excessive contact with skin will cause irritation. Rinse skin thoroughly if this occurs.

DETAILED RISK ASSESSMENTS CAN BE SUPPLIED ON REQUEST

Bag Size (Kg)	Mix Water (± litres)
20	2

Note: These figures are for guidance only.

ADDITIONAL INFORMATION

Any quantity of this concrete mix may be produced as desired on site, making it ideal when work is undertaken from shaft conveyances and avoiding waste.

It is easy to use – suitable for both machine bases and grouting in buntions.

Repairing a shaft no longer needs to be inefficient and time-consuming. Bunton Bagcrete 30 gives you a perfect solution in every 20 kilogram polypropylene bag.